

Product datasheet BIOCRYL® C

1 Description of the product / intended use / company

Trade name: **BIOCRYL® C**

Intended use: Thermoplastic foils for the manufacture of appliances and splints for dental and orthodontic treatments.

Manufacturer / Supplier: Scheu Dental GmbH
Am Burgberg 20
58642 Iserlohn
Germany
Tel. 0049 2374 9288-0

2 Composition / information on ingredients

Chemical characterization

CAS-Number: 9011-14-7
Designation: Polymethylmethacrylat (PMMA)

3 Handling and storage

Handling

Information for safe handling: When using do not eat, drink or smoke.
Provide suction extractors if dust is formed.

Storage

Storage conditions: Store dry and dark at 5 - 35 °C

4 Physical, chemical, mechanical and biological properties

4.1 General properties

Properties	Guideline	Value
Form	-	Solid
Colour	-	Depending on the version, transparent or colored
Odour	-	Odourless
Density	ISO 1183	1,19 g/cm ³
Water absorption after 24 h at 23°C	-	-

Product datasheet BIOCRYL® C

4.2 Mechanical properties

Properties	Guideline	Value
Tensile strength	ISO 527	76 MPa
Tensile modulus	ISO 527	3200 MPa
Elongation at break	ISO 527	5,5 %
Charpy Impact Strength @ 23 °C	ISO 179/1eU	20 kJ/m ²

4.3 Thermal properties

Properties	Guideline	Value
Glass transition temperature	ISO 11357	112 °C
Vicat softening point	ISO 306	103 °C

4.4 Biological properties / Biocompatibility

A biological evaluation was carried out for the material in accordance with DIN EN ISO 10993-1. It meets the requirements regarding biocompatibility for medical devices.

5 Stability and reactivity

Thermal decomposition / Conditions to avoid:

No decomposition by intended use.

6 Disposal

The material can be recycled after separation or disposed of like commercial or household waste.

The aforementioned data are given most conscientiously but without any obligation. Any processing details are provided merely for guidance: it is the user's responsibility to check the suitability of the product for the intended application.